

1. Introduction

HANWHA P-800 is a PVC homopolymer of particular interest in rigid applications. P-800 has established a deserved reputation for low fish-eye count, excellent fusion properties and exceptional early color heat stability. It is recommended for sheet, profile, fitting, rigid sheet & film manufacturing.

2. Applications

Rigid sheet & film, Rigid plate, Rigid profile, Injection molding, Fitting, Rigid foam profile

3. Properties

Properties	Unit	Typical value	Methods
Degree of polymerization	-	800±50	JIS K 6720-2
K-Value	-	61	DIN 53726
Apparent bulk density	g/cm ³	0.55±0.04	ASTM D1895
Volatility	%	Max 0.30	ASTM D3030
Sieve analysis (45 Mesh on)	%	Max 0.3	ASTM D1921

※ The values given above are typical test results which should be used as a guide only. They do not form the whole or part of a specification or guarantee.

4. Storage, Packaging, Safety

Storage

P-800 should be stored dry conditions and at room temperature below 25°C.

Safety and Handling

The Hanwha Solutions Corporation provides its customers with a product specific Material Safety Data Sheet (MSDS) to cover potential health effects, safe handling, use and transportation. Hanwha Solutions Corporation strongly encourage its customers to review MSDS on its products and other materials prior to their use. P-800 is normally supplied as a power in 25kg polypropylene inner coated paper bag, 500kg flecon bag as well as in bulk form.

P-800 is not formulated to contain any hazardous or regulated materials such as lead, cadmium, mercury, and chromium compounds. And Hanwha Solutions Corporation guarantee that P-800 does not include any hazardous or regulated materials during the manufacturing process.

General Information

The data and recommendations contained in this brochure represent the current state of our knowledge and serve as a guide only to our products and their potential applications. Therefore, no warranty of specific properties of the products mentioned herein nor of their suitability or fitness for a particular purpose is implied.

Further information and recommendations for processing can be obtained from our technical support staff and representatives.