

SOLURYL RW-114

Self-crosslink acrylic copolymer emulsion for use in water-based 1K wood coating

Features

- Non Film Forming Emulsion
- Excellent Hardness
- Good Appearance
- Compatibility with Soluryl Emulsions

Typical properties

Properties	Specification
Appearance	Translucent emulsion
Molecular Weight	>200,000
Non Volatiles, wt%	41.5
Acid Number, mg KOH/g	21
Tg, °C	82
Density, g/ml	1.03
pH	8.6
Viscosity, cps (25°C, Brookfield)	100
Freeze/Thaw Stability	5 cycles

Recommendation for end-use

- Special emulsion as additives for top coating of wood substrate
 - ✓ Mix with Soluryl Emulsions, 15~25wt%, prefer 20wt%
(Add more 0.5wt% coalescent agent to make up film forming property)
 - ✓ To enhance the hardness
 - ✓ To get better the appearance such as gloss and transparency

Safety information

Soluryl RW-114 is not formulated to contain any hazardous or regulated materials such as lead, cadmium, mercury and chromium compounds. And raw materials for Soluryl RW-114 and our manufacturing process do not include any hazardous or regulated materials.

The information given herein and other otherwise supplied to users is based on our general experience and where applicable, on the results of tests on samples of typical manufacture. However, because of the many factors which are outside knowledge and control, which can effect the use of these products, users must rely on their own judgment and we cannot accept liability for any injury, loss or damage resulting from reliance upon such information.