

## Ethylene Vinylacetate Copolymer

Blown Film Grade

<b>MELT INDEX</b>	<b>0.8</b>
<b>VA CONTENT</b>	<b>6.5</b>
<b>DENSITY</b>	<b>0.927</b>

HANWHA EVA 2030 is manufactured by DOW high pressure tubular process and designed for a variety of film applications such as multilayer agricultural film. EVA 2030 has well-balanced properties of high clarity, mechanical properties and processability.

This product complies with U.S. FDA regulation 21 CFR 177.1350(a)(1).

### ▣ Outstanding Properties

Excellent processability  
Good optical property  
Good mechanical properties

### ▣ Processing Conditions

Melt temperature: 140 ~ 180°C  
Blow-up ratio: 2 ~ 3  
Optimum gage range: 0.05~0.1 mm

### ▣ Additives

Antioxidant, Slip agent, Anti-blocking agent

### ▣ Physical Properties

Physical Properties	Unit	Test Method	Value
Melt Index	g/10min	ASTM D1238	0.8
VA Content	wt%	HCC Method	6.5
Density	g/cm <sup>3</sup>	ASTM D1505	0.927
Vicat Softening Point	°C	ASTM D1525	83
Melting Point	°C	ASTM D3417	101
Tensile Strength at Break	kg/cm <sup>2</sup>	ASTM D638	190
Elongation at Break	%	ASTM D638	740
Brittleness Temperature, F <sub>0</sub>	°C	ASTM D746	<-76

<b>Film Properties</b>		<b>Unit</b>	<b>Test Method</b>	<b>Value</b>
Film Thickness		Mm	HCC Method	0.06
Tensile Strength at Break	MD	kg/cm <sup>2</sup>	ASTM D882	260
	TD			240
Elongation at Break	MD	%	ASTM D882	350
	TD			650
Tensile Tear Strength	MD	kg/cm	ASTM D1004	85
	TD			90
Dart Impact Strength		g	ASTM D1709	>400
Haze		%	ASTM D1003	4.0

1. These are typical properties: not to be construed as specification.
2. The value for this property is dependent on part geometry and fabrication conditions.