



CHNA-8380L

Wire & Cable Compound

HDPE for Solid/Skin Insulation

Melt Index

0.7

Density

0.945

Description

CHNA-8380L is a high molecular weight, high density polyethylene insulation compound specially formulated to provide an excellent oxidative stability, physical/electrical properties. It provides superior long term aging performance especially in jelly-filled cable applications. It meets Telcordia (Bellcore) aging test requirements, as well as all major international aging test specifications for both solid and foam/skin insulation.

Applications

CHNA-8380L can be used for the full range of telephone cable insulation including air-core and jelly-filled and LAN cable.

Specifications

CHNA-8380L meets the applicable requirements as below when processed using sound extrusion practice and testing procedure:

ASTM D1248 Type III, Class A, Category 4, Grade E8, E9
Telcordia GR-421(Bellcore)
BS 6234 : Type H03
IEC 60708

ISO 1872-PE, KCHL, 45 D-006
NF C32-060

Physical Properties	Unit	Test Method	Typical Value
Melt Index	g/10min.	ASTM D1238	0.7
Density	g/cm ³	ASTM D1505	0.945
Tensile Strength	kg/cm ²	ASTM D638	240
Elongation	%	ASTM D638	550
Oven Aging @ 100°C, 48 hours			
Retention of Tensile Strength	%	ASTM D638	>90
Retention of Elongation	%	ASTM D638	>90
ESCR, F ₀ @ 50°C, 10% Igepal	hrs	ASTM D1693	>1,000
Low Temperature Brittleness	°C	ASTM D746	<-76



Hardness (Shore D, 1 sec.)	-	ASTM D2240	53
Oxidative Induction Time(200°C, Al)	min.	ASTM D3895	>200

Electrical Properties	Unit	Test Method	Typical Value
Dielectric Constant @ 1 MHz	-	ASTM D150	<2.3
Dissipation Factor @ 1 MHz	-	ASTM D150	<0.0006
DC Volume Resistivity	ohm cm	ASTM D257	>10 ¹⁶

1) These are typical properties and are not to be regarded as specifications.

2) Under 50 mm/minute testing speed by molded / dumbbell shaped sheet

Processing Guidelines

CHNA-8380L provides excellent surface finish and higher output rates over a broad range of conditions. A range of extrusion temperature in processing condition is 180~240 °C.

Storage

The material should be stored indoors (10~30°C) in closed original packages in clean and dry environment. It is recommended that the using of the product on a first-in, first-out basis be established. Then recommended storage time at customer should not exceed 1 year.

Quality Systems

Hanwha maintains a quality management system according to ISO 9001. This system provides traceability of individual batches and their production. If process is changed in a way that suspected to change the properties of the product, Hanwha will provide adequate information to the customer.

Certificate

Based on quality inspection data at production, Hanwha supplies an inspection certificate for each batch. The certificate contains:

Product name
Batch number
Production date
etc.

Data Sheet and Safety

Most data sheets and safety data sheets are available on Hanwha web site, <http://hcc.hanwha.co.kr>. Please contact your Hanwha representative for more details on various aspects of safety, recovery and disposal of the product.

