CTBA-8760BK

Wire & Cable Compound

Conductor and Insulation Shield

Density

1.11

Description

CTBA-8760BK is a semiconductive compound and has an excellent electrical conductivity, scorch stability and surface smoothness.

Applications

CTBA-8760BK can be used for bonded typed, conductor and insulation shielding of high voltage up to 525 kV direct current power cables.

Specifications

CTBA-8760BK meets the applicable requirements as below when processed using sound extrusion practice and testing procedure:

Physical Properties	Unit	Test Method	Typical Value
Density	g/cm ³	ASTM D1505	1.11
Tensile Strength	kg/cm ²	ASTM D638	>150
Elongation	%	ASTM D638	>200
Oven Aging @ 135 °C, 7 days			
Retention of Tensile Strength	%	ASTM D638	>90
Retention of Elongation	%	ASTM D638	>85
Hot/Set @ 200°C, 20N/cm ²		IEC 60811-2-1	
Hot Elongation	%		<100
Permanent Set	%		<10

Electrical Properties	Unit	Test Method	Typical Value
DC Volume Resistivity			
23 °C	ohm cm	ASTM D991	<100
90 °C	ohm cm	ASTM D991	<500

¹⁾ These are typical properties and are not to be regarded as specifications.

²⁾ Under 250 mm/minute testing speed by molded / dumbbell shaped sheet



Processing Guidelines

CTBA-8760BK provides excellent surface finish and higher output rates over a broad range of conditions. For optimum results, melt extrusion temperatures in the range of 120~130 °C is recommended. If needed, hopper drying at 50~60 °C for 3~5 hours is recommended to remove moisture.

Storage

The material should be stored indoors($10\sim30^{\circ}$ C) in closed original packages in clean and dry environment. It is recommended that the using of the product on a first-in, first-out basis be established. Then recommended storage time at customer should not exceed 1 year.

Quality Systems

Hanwha maintains a quality management system according to ISO 9001. This system provides traceability of individual batches and their production. If process is changed in a way that suspected to change the properties of the product, Hanwha will provide adequate information to the customer.

Certificate

Based on quality inspection data at production, Hanwha supplies an inspection certificate for each batch. The certificate contains:

Product name Batch number Production date etc.

Data Sheet and Safety

Most data sheets and safety data sheets are available on Hanwha web site, http://hcc.hanwha.co.kr Please contact your Hanwha representative for more details on various aspects of safety, recovery and disposal of the product.

